


Special technology  
**for better hail resistance**  
with unique solar colors  
only from Palram



### Main Benefits

- UV Protection
- Hail resistance - 50% more than regular corrugated sheet
- 100% diffused light
- High wind and snow load resistance
- Extended warranty












## Typical Applications

- Pergolas and gazebos
- Carports
- Patio enclosures
- Covered walkways
- Sunrooms
- Canopies and overhangs

## Product Availability

<b>Colors</b>	Clear, Bronze, Solar Ice, Solar Control, Solar Olympic, Grey
<b>Textures</b>	Prismatic-honeycomb
<b>Thickness</b>	2.8 mm
<b>Width</b>	1045 mm
<b>Profile</b>	76/18 Iron/Sinus 

					
<b>Clear</b>	<b>Bronze</b>	<b>Solar Ice</b>	<b>Solar Control</b>	<b>Solar Olympic</b>	<b>Grey</b>
87% Light Transmission	33% Light Transmission	25% Light Transmission	20% Light Transmission	25% Light Transmission	60% Light Transmission

## Flammability

SUNTUF® BH complies with the most demanding international fire resistance standards in the field of plastics, as indicated in the detailed table herein. The classification is subject to product type, thickness and color.

Standard	*Classification
AS/NZS 1530.3	Approved
EN13501	B, s1, d0
NFP 92501, 4, 5	M-1
DIN 4102	B-1
UL 723	4.7, 47.0
Los Angeles Building Code	CC2 (Section 2603)
UNI 9177, 9176	Class 2

\* For more detailed information please contact your Palram distributor.

## Typical Physical Properties

Property	Method*	Conditions	Units	Value
Density	D-792		g/cm <sup>3</sup>	1,2
Heat deflection temperature (H.D.T)	D-648	Load: 1.82 MPa	°C	135
Service Temperature Range (Short term)			°C	-50 to +120
Service Temperature Range (Long term)			°C	-50 to +100
Coefficient of linear thermal expansion	D-696		cm/cm°C	6.5 x 10 <sup>-5</sup>
Thermal conductivity	C-177		W/m K	0.21
Tensile strength at yield	D-638	10 mm/min	MPa	62
Tensile strength at break	D-638	1 mm/min	MPa	65
Elongation at yield	D-638	10 mm/min	%	6
Elongation at break	D-638	10 mm/min	%	>70
Tensile modulus of elasticity	D-638	1 mm/min	MPa	2,300
Flexural strength mechanical	D-790	1 mm/min	MPa	93
Flexural modulus	D-790	1.3 mm/min	MPa	1,890
Impact falling weight	(ISO 6603/1 E50)	2.8 mm sheet	J	75
Rockwell hardness	D-785		R Scale	118
Light transmission	D-1003	Clear sheet	%	90%
Haze	D-1003	Clear sheet	%	<0.5
Yellowness index	D-1003	Clear sheet	YI	<1

\* ASTM method except where noted otherwise

## Load / Span Data

Load (kg/m <sup>2</sup> )	Maximum Roof Span (mm) 2.8 mm Thickness
50	1400
75	1300
100	1200
125	1175
150	1150
175	1125
200	1100



**PALRAM H.Q.**  
Tel: +972 4 8459900  
Fax: +972 4 8444012  
palram@palram.com  
www.palram.com

**PALRAM EUROPE LTD.**  
Tel: +44 1302 380777  
Fax: +44 1302 380788  
sales.europe@palram.com

**PALRAM AMERICAS**  
Tel: 610 2859918  
Fax: 610 2859928  
palramamericas@palram.com  
www.palram.com/us/



79024 - 11.2021

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

©1997 Palram Industries Ltd. | SUNTUF® is a trademark of Palram Industries Ltd.



www.palram.com